



**DESULFURISASI OKSIDATIF DIBENZOTIOFENA MENGGUNAKAN  
KATALIS MoOX TERIMPREGNASI PADA PASIR SILIKA MAGNETIK  
DARI PANTAI PARANGTRITIS**

Fidela Dini Rahmasari

18/424219/PA/18324

**INTISARI**

Penelitian desulfurisasi oksidatif dibenzotiofena (DSO-DBT) menggunakan katalis  $\text{MoO}_x$  terimpregnasi pada pasir silika magnetik dari pantai Parangtritis ( $\text{MoO}_x\text{-PP}$ ) telah dilakukan. Penelitian dilakukan dengan tujuan mempelajari karakter pasir silika magnetik dari Parangtritis (PP) dan katalis  $\text{MoO}_x\text{-PP}$ , serta aktivitas katalis pada reaksi DSO-DBT dengan variasi temperatur dan waktu reaksi, serta volume  $\text{H}_2\text{O}_2$ . Preparasi katalis  $\text{MoO}_x\text{-PP}$  dilakukan dengan menggunakan metode impregnasi basah. Katalis  $\text{MoO}_x\text{-PP}$  dikarakterisasi menggunakan XRD, SEM-EDX, SAA, FTIR, dan TEM dan diuji keasamannya dengan metode adsorpsi uap basa  $\text{NH}_3$  secara gravimetri. Variasi yang dilakukan terdiri dari temperatur reaksi 30, 40, 50, dan 60 °C. Waktu reaksi divariasi 10, 20, 30, dan 40 menit. Variasi volume  $\text{H}_2\text{O}_2$  sebesar 0,21; 0,42; dan 0,63 mL. Produk DSO-DBT dikarakterisasi dengan spektrofotometer UV-Vis.

Katalis PP dan  $\text{MoO}_x\text{-PP}$  memiliki total keasaman sebesar 1,48 dan 3,07 mmol/g. Kedua katalis memiliki sifat magnet yang ditunjukkan dengan dapat ditarik magnet. Katalis  $\text{MoO}_x\text{-PP}$  menunjukkan pola difraktogram dengan puncak  $\text{SiO}_2$ ,  $\text{MoO}_3$ , dan  $\text{Fe}_3\text{O}_4$ . Katalis  $\text{MoO}_x\text{-PP}$  memiliki morfologi berbentuk bulatan atau bola dengan permukaan yang kasar, ukuran tidak beraturan, dan terbentuk aglomerasi. Luas permukaannya adalah 4,506  $\text{m}^2/\text{g}$  dengan volume pori 0,034  $\text{cm}^3/\text{g}$ , dan diameter pori 30,044 nm yang termasuk ke dalam material mesopori. Aktivitas katalis  $\text{MoO}_x\text{-PP}$  dari reaksi DSO-DBT (83,35 %) optimum pada variasi temperatur dan waktu reaksi 40 °C dan 30 menit, dan volume  $\text{H}_2\text{O}_2$  0,42 mL. Aktivitas katalis PP pada reaksi DSO-DBT sebesar 77,20 % pada temperatur dan waktu reaksi 40 °C dan 30 menit, dan volume  $\text{H}_2\text{O}_2$  0,42 mL.

Kata kunci: desulfurisasi oksidatif, dibenzotiofena,  $\text{MoO}_x$ , pasir pantai Parangtritis.



***OXIDATIVE DESULFURIZATION OF DIBENZOTHIOPHENE USING  
MoO<sub>x</sub> CATALYST IMPREGNATED ON MAGNETIC SILICA SAND FROM  
PARANGTRITIS BEACH***

Fidela Dini Rahmasari

18/424219/PA/18324

**ABSTRACT**

Research on oxidative desulfurization of dibenzothiophene (DSO-DBT) using MoO<sub>x</sub> catalyst impregnated on magnetized silica sand from Parangtritis beach (MoO<sub>x</sub>-PP) has been carried out. The research was conducted with the aim of studying the character of the magnetic silica sand from Parangtritis (PP) and MoO<sub>x</sub>-PP catalyst and the catalyst activity on ODS-DBT reaction under variations of temperature and time reaction as well as volume of H<sub>2</sub>O<sub>2</sub>. The preparation of MoO<sub>x</sub>-PP catalyst was conducted using wet impregnation method. The MoO<sub>x</sub>-PP catalyst was characterized using XRD, SEM-EDX, SAA, FTIR, and TEM and gravimetrically tested for acidity using NH<sub>3</sub> base vapor adsorption. The variations of reaction times was 10, 20, 30, and 40 min. The reaction temperature was varied from 30, 40, 50, to 60 °C. The volume of H<sub>2</sub>O<sub>2</sub> was conducted in a variation of 0.21; 0.42; and 0.63 mL. The result of ODS-DBT reaction was characterized by UV-Vis spectrophotometer.

The results showed that the P and MoO<sub>x</sub>-PP catalysts have a total acidity of 1,48 and 3.07 mmol/g. The P and MoO<sub>x</sub>-PP catalyst had magnetic properties as evidenced by being attracted to a magnet. The diffractogram pattern showed the peaks of SiO<sub>2</sub>, MoO<sub>3</sub>, and Fe<sub>3</sub>O<sub>4</sub> on MoO<sub>x</sub>-PP catalyst. The MoO<sub>x</sub>-PP catalyst has a spherical morphology with a rough surface, irregular size, and agglomeration forms with surface area of 4.506 m<sup>2</sup>/g, pore volume of 0.034 cm<sup>3</sup>/g, and average pore diameter of 30.044 nm. The optimum catalyst activity of MoO<sub>x</sub>-PP on ODS-DBT reaction (83.35 wt%) resulted in a temperature of 40 °C, time of 30 min, and H<sub>2</sub>O<sub>2</sub> volume of 0.42 mL. The activity of P catalyst on ODS-DBT reaction was 77.20 wt% on a temperature of 40 °C, time of 30 min, and H<sub>2</sub>O<sub>2</sub> volume of 0.42 mL.

Keywords: dibenzothiophene, MoO<sub>x</sub>, oxidative desulfurization, Parangtritis beach sand.