

INTISARI

Pengaruh Konsentrasi Co Terhadap Struktur Kristal dan Sifat Magnetik Nanopartikel $\text{Co}_x\text{Ni}_{1-x}\text{Fe}_2\text{O}_4$ yang Disintesis dengan Metode Kopresipitasi

Joko Utomo

15/388387/PPA/04826

Cobalt mensubstitusi nanopartikel nickel ferit ($\text{Co}_x\text{Ni}_{1-x}\text{Fe}_2\text{O}_4$) dengan komposisi stokiometri (x) dari 0,2 hingga 0,8 telah berhasil disintesis dengan metode kopresipitasi pada suhu sintesis 90 °C. Ukuran kristalit nanopartikel $\text{Co}_x\text{Ni}_{1-x}\text{Fe}_2\text{O}_4$ pada rentang 14 – 27 nm. Analisis *X-Ray Diffraction* (XRD) menunjukkan parameter kisi untuk $x=0,3$ adalah 8,423 Å, dan kemudian meningkat seiring dengan peningkatan konsentrasi Co. Hal ini dikarenakan substitusi ion Co dengan jari-jari ion yang lebih besar. Pola *Selected Area Electron Diffraction* (SAED) menunjukkan bahwa peningkatan konsentrasi Co memperlihatkan cincin difraksi lebih terang yang mana mengindikasikan derajat kristalinitas yang lebih tinggi. Hal ini dapat dikonfirmasi dari cincin difraksi untuk $x=0,7$ lebih terang daripada $x=0,3$ dan $x=0,5$. Pola SAED juga memperlihatkan bahwa nanopartikel $\text{Co}_x\text{Ni}_{1-x}\text{Fe}_2\text{O}_4$ berupa polikristalin. Spektra *Fourier Transform Infrared Spectroscopy* (FTIR) pada nanopartikel $\text{Co}_x\text{Ni}_{1-x}\text{Fe}_2\text{O}_4$ menunjukkan adanya vibrasi pada ion logam pada interval bilangan gelombang 370.33 cm^{-1} – 601.79 cm^{-1} pada sub ruang tetrahedral dan oktahedral. Serapan tersebut mengindikasikan formasi struktur spinel ferit. Hasil histeresis menunjukkan bahwa besar magnetisasi maksimum dengan medan magnet luar maksimum 15 kOe pada nanopartikel $\text{Co}_x\text{Ni}_{1-x}\text{Fe}_2\text{O}_4$ untuk $x=0,2$ adalah 7,0 emu/g, dan kemudian meningkat hingga 29,0 emu/g untuk $x=0,8$ seiring dengan peningkatan konsentrasi Co. Hasil ini dapat dihubungkan dengan substitusi Co^{2+} yang memiliki momen magnetik lebih tinggi. Koersivitas (H_c) pada nanopartikel $\text{Co}_x\text{Ni}_{1-x}\text{Fe}_2\text{O}_4$ untuk $x=0,2$ adalah 59,4 Oe dan kemudian meningkat hingga 641,75 Oe untuk $x=0,6$ seiring peningkatan konsentrasi Co. Hal ini dikarenakan Cobalt memiliki magnetik anisotropik lebih tinggi daripada Nickel.

Kata Kunci : $\text{Co}_x\text{Ni}_{1-x}\text{Fe}_2\text{O}_4$, spinel, ferit, nanopartikel magnetik

ABSTRACT

Effect of Co Concentration on Crystal Structures and Magnetic Properties of $\text{Co}_x\text{Ni}_{1-x}\text{Fe}_2\text{O}_4$ Nanoparticles Synthesized by Co-Precipitation Method

Joko Utomo

15/388387/PPA/04826

Cobalt substituted nickel ferrite nanoparticles ($\text{Co}_x\text{Ni}_{1-x}\text{Fe}_2\text{O}_4$) with stoichiometric proportion (x) from 0.2 to 0.8 have been synthesized by co-precipitation method with synthesis temperature of 90 °C. The crystallite size of $\text{Co}_x\text{Ni}_{1-x}\text{Fe}_2\text{O}_4$ nanoparticles were within range of 14 - 27 nm. The X-ray diffraction (XRD) analysis informed that the lattice parameter of $\text{Co}_x\text{Ni}_{1-x}\text{Fe}_2\text{O}_4$ nanoparticles at $x=0.3$ was 8.423 Å, and then increased with increasing Co concentration. This is due to substitution of larger ionic radius of Co^{2+} . The selected area electron diffraction (SAED) patterns showed that increasing Co concentration exhibited more prominent ring indicating well crystallinity. It could be confirmed from the crystallinity of the sample for $x=0.7$ was higher than 0.3 and 0.5. The SAED patterns of $\text{Co}_x\text{Ni}_{1-x}\text{Fe}_2\text{O}_4$ nanoparticles also displayed polycrystalline diffraction ring. The fourier transform infrared spectroscopy (FTIR) spectra of $\text{Co}_x\text{Ni}_{1-x}\text{Fe}_2\text{O}_4$ showed the presence of vibration bands of metal ions within the range of $370.33 \text{ cm}^{-1} - 601.79 \text{ cm}^{-1}$ at the tetrahedral and octahedral sites, respectively. These two bands indicated the formation of a spinel ferrite structure. The hysteresis results showed that the maximum magnetization at 15 kOe of $\text{Co}_x\text{Ni}_{1-x}\text{Fe}_2\text{O}_4$ nanoparticles at $x=0.2$ was 7.0 emu/g, and then increase to 29.0 emu/g at $x=0.8$ with increasing Co concentration. The results could be attributed to substitution of higher magnetic moment of Co^{2+} . The coercivity (H_c) of $\text{Co}_x\text{Ni}_{1-x}\text{Fe}_2\text{O}_4$ nanoparticles at $x=0.2$ was 59.4 Oe, and then increase to 641,75 Oe at $x=0.6$ with increasing Co concentration. This is due to cobalt having higher magnetic anisotropy than nickel.

Keyword : $\text{Co}_x\text{Ni}_{1-x}\text{Fe}_2\text{O}_4$, spinel, ferrite, magnetic nanoparticles